



## **T-Rex Transparent**

Revision: 18/10/2022 Page 1 from 2

#### **Technical data**

10011110ui uutu	
Basis	Acrylic
Consistency	Paste
Curing system	Physical drying
Density	Ca. 1,05 g/ml
Temperature resistance**	$-20  ^{\circ}\text{C} \rightarrow 70  ^{\circ}\text{C}$
Open time (23°C, 55% RV)*	15 min.
Initial tack	Minimum 125 kg/m²
End strength wood-wood	Ca. 22 kg/cm <sup>2</sup>
End strength wood-aluminium	Ca. 16 kg/cm <sup>2</sup>
End strength wood-PVC	Ca. 12 kg/cm <sup>2</sup>
Application temperature	$5  ^{\circ}\text{C} \rightarrow 30  ^{\circ}\text{C}$

<sup>\*</sup> These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. \*\* This information relates to fully cured product.

## **Product description**

T-Rex Transparent is a solvent free and fibre reinforced high strength construction adhesive with high initial grab (over 125kg/m²) and high bond strength. Extremely suitable for porous surfaces.

#### **Properties**

- Fibre reinforced
- White when extruded, transparent after curing
- Initial tack: 125 kg/m² (full surface bonding)
- Meets GEV EMICODE EC-1 PLUS: very low emission
- Excellent adhesion on many porous materials both in interior and exterior applications.
- Suitable for bonding on uneven surfaces.
- Ecologic
- Direct application onto one substrate

## **Applications**

- Very good adhesion on all usual porous building surfaces.
- Suitable for solid fixing of materials like wood, synthetic materials, stone, wall tiles, metal on surfaces of concrete, stone, plasterwork, wood, chipboard etc.

 Suitable for bonding panel work, panels, skirting boards of wood and PVC, cable tray and the most frequent decoration materials.

#### **Packaging**

Colour: white, dries transparent Packaging: 310 gram

## Shelf life

At least 24 months in original, unopened packaging at a cool and dry storage place, between +5°C and +25°C.

#### **Substrates**

Substrates: all usual building substrates Nature: clean, free of dust and grease. At least one of the materials to be bonded must be porous.

Surface preparation: No pretreatment required. There is no adhesion on PE, PP, PTFE (Teflon®) and bituminous substrates. We recommend a preliminary adhesion test on any substrate.

## **Application method**

Application method: Apply the adhesive by means of a caulking gun in equal beads or dots on one of the materials that have to be glued. Always apply a bead on the edges of the components and on edges and corners of

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

 Soudal NV
 Everdongenlaan 18 - 20
 B-2300 Turnhout, Belgium

 Tel: +32 (0)14-42.42.31
 Fax: +32 (0)14-42.65.14
 www.soudal.com





# **T-Rex Transparent**

Revision: 18/10/2022 Page 2 from 2

panels. Press the surfaces immediately together and batten down with a rubber hammer. Support if needed. The bond may be loaded after 24-48h. Cleaning: Before curing, T-Rex Transparent can be removed with water from substrates and tools. Cured T-Rex Transparent can only be removed mechanically. Repair: With the same material.

## **Health- and Safety Recommendations**

Take the usual labour hygiene into account. Consult the packaging label for more information.

## Remarks

- The applied pressure and not the duration of the compression will determine the ultimate strength of the bond.
- Do not use in applications where continuous water immersion is possible.
- In case of short term water exposure (24 hrs) a slight 'clouding' will occur.
- In case of long term water exposure (14 days) the product will get white again and lose its mechanical properties.

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

 Soudal NV
 Everdongenlaan 18 - 20
 B-2300 Turnhout, Belgium

 Tel: +32 (0)14-42.42.31
 Fax: +32 (0)14-42.65.14
 www.soudal.com